



# ACRIMAX®

Multi-surface



AcriMax is our multi-surface, interior/ exterior waterborne acrylic coating. Suitable for commercial and light industrial applications, it has excellent adhesion to a variety of substrates including properly prepared metal and masonry. AcriMax is quick drying and has early block resistance and hardness for projects where down-time needs to be kept to a minimum. From doors and windows to hand rails, cabinets and floors, AcriMax is a truly versatile product.

- Self-priming directly to multiple surfaces
- Excellent early block resistance and hardness
- Dries quickly
- Excellent adhesion to slick and glossy surfaces
- Water clean-up

## EGGSHELL

Ideal for projects where a deep, rich look is desired yet only a minimal sheen is needed. It is designed for areas that require minimal washability and have limited use.

## SEMIGLOSS

This high-sheen product is very washable and perfect for areas that are more susceptible to dirt, grease, and moisture. Ideal for projects in high traffic areas.



# ACRIMAX®

Multi-surface



## Specifications For Acrimax

	EGGSHELL	SEMIGLOSS
Volume Solids	39 +/- 2%	30%
VISCOSITY	90-95 KU	95-100 KU
Weight Per Gallon	10.6 (LB)	10.48 (LB)
Gloss	20-25% @ 85°	55-65% @ 60°
V.O.C. (minus water)	<150 g/L	125 g/L

**COVERAGE:** Approximately 350 square feet per gallon @ 1.5 dry mils. Two coats recommended for even coverage. Coverage depends on porosity and profile of the surface.

**DRY TIME:** One hour to touch and four hours to recoat @ 70°F and 50% relative humidity.

## ABOUT MILLER PAINT

Established in 1890, Miller Paint is an employee owned company with a proud Northwest tradition of creating products made for our unique Northwest climate. From our humble beginnings as a family-run company, to a company with over 300 employees and over 50 locations, Miller Paint has always been there for the professional and homeowner alike.

For a location near you, go to [www.millerpaint.com](http://www.millerpaint.com)

Specification figures should be taken as accurate for products being produced at the time of publication in untinted white bases only. Formulation improvements may be made from time to time that may affect these figures to some degree. Manufacturing tolerances of +/-2% are considered acceptable. Whenever a change is made that the Manufacturer considers substantial, the specification will be revised. Miller and Miller Paints are registered trademarks of Miller Paint Co., Inc. Portland, OR. REV 9/16